

# S-BAL14

Code(d) **569563**

Code(e) **571561**

Refractive Index $n_d$	<b>1.56883</b>	Abbe Number $\nu_d$	<b>56.36</b>	Dispersion $n_F-n_C$	<b>0.010092</b>
	1.568832				
Refractive Index $n_e$	1.571237	Abbe Number $\nu_e$	56.09	Dispersion $n_F-n_C'$	0.010185

Refractive Indices		
$\lambda(\mu\text{m})$		
$n_{2325}$	2.32542	1.54050
$n_{1970}$	1.97009	1.54565
$n_{1530}$	1.52958	1.55116
$n_{1129}$	1.12864	1.55601
$n_t$	1.01398	1.55761
$n_s$	0.85211	1.56040
$n_{A'}$	0.76819	1.56230
$n_f$	0.70652	1.56404
$n_C$	0.65627	1.56577
$n_{C'}$	0.64385	1.56626
$n_{\text{He-Ne}}$	0.6328	1.56671
$n_D$	0.58929	1.56874
$n_d$	0.58756	1.56883
$n_e$	0.54607	1.57124
$n_F$	0.48613	1.57587
$n_{F'}$	0.47999	1.57645
$n_{\text{He-Cd}}$	0.44157	1.58067
$n_g$	0.435835	1.58141
$n_h$	0.404656	1.58604
$n_i$	0.365015	1.59400

Constants of Dispersion Formula	
$A_1$	1.27553696E+00
$A_2$	1.46083393E-01
$A_3$	1.16754699E+00
$B_1$	7.49692359E-03
$B_2$	3.10421530E-02
$B_3$	1.28947092E+02

Chemical Properties	
Water Resistance(Powder) Group RW(P)	2
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	2~3
Acid Resistance(Surface) Group SR	1.0
Phosphate Resistance PR	2.0

Mechanical Properties	
Young's Modulus E (GPa)	81.1
Rigidity Modulus G (GPa)	32.7
Poisson's Ratio $\sigma$	0.240
Knoop Hardness Hk(Class)	570   6
Abrasion Aa	140

Partial Dispersions	
$n_C-n_t$	0.008164
$n_C-n_{A'}$	0.003476
$n_d-n_C$	0.003057
$n_e-n_C$	0.005462
$n_g-n_d$	0.012574
$n_g-n_F$	0.005539
$n_h-n_g$	0.004629
$n_i-n_g$	0.012595
$n_C-n_t$	0.008650
$n_e-n_{C'}$	0.004976
$n_{F'}-n_e$	0.005209
$n_i-n_{F'}$	0.017555

Relative Partial Dispersions	
$\theta_{C,t}$	0.8090
$\theta_{C,A'}$	0.3444
$\theta_{d,C}$	0.3029
$\theta_{e,C}$	0.5412
$\theta_{g,d}$	1.2459
$\theta_{g,F}$	0.5489
$\theta_{h,g}$	0.4587
$\theta_{i,g}$	1.2480
$\theta'_{C,t}$	0.8493
$\theta'_{e,C}$	0.4886
$\theta'_{F,e}$	0.5114
$\theta'_{i,F'}$	1.7236

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta \theta_{C,t}$	-0.0021
$\Delta \theta_{C,A'}$	0.0002
$\Delta \theta_{g,d}$	-0.0018
$\Delta \theta_{g,F}$	-0.0014
$\Delta \theta_{i,g}$	-0.0051

Thermal Properties	
Strain Point StP (°C)	533
Annealing Point AP (°C)	562
Transformation Temperature Tg (°C)	580
Yield Point At (°C)	622
Softening Point SP (°C)	700
Expansion Coefficients (-30~+70°C)	80
$\alpha$ ( $10^{-7} \text{K}^{-1}$ ) (+100~+300°C)	93
Thermal Conductivity $\lambda$ W/(m·K)	0.967

Coloring			
$\lambda_{80}$	360	$\lambda_5$	325
$\lambda_{70}$			

Internal transmission			
$\lambda_{0.80}$	354	$\lambda_{0.05}$	329

CCI		
B	G	R
0.00	0.26	0.24

Internal Transmittance	
$\lambda(\text{nm})$	$\tau$ 10mm
280	
290	
300	
310	
320	
330	0.09
340	0.44
350	0.74
360	0.88
370	0.946
380	0.970
390	0.983
400	0.989
420	0.992
440	0.993
460	0.994
480	0.995
500	0.997
550	0.998
600	0.998
650	0.997
700	0.998
800	0.998
900	0.998
1000	0.997
1200	0.997
1400	0.989
1600	0.993
1800	0.983
2000	0.967
2200	0.914
2400	0.86

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	$\Delta n/\Delta T$ relative ( $10^{-6}\text{K}^{-1}$ )						
	t	C'	He-Ne	D	e	F'	g
-40~-20	1.2	1.5	1.5	1.6	1.8	2.1	2.4
-20~ 0	1.2	1.5	1.6	1.7	1.8	2.2	2.5
0~20	1.3	1.6	1.6	1.7	1.9	2.2	2.6
20~40	1.3	1.7	1.7	1.8	2.0	2.3	2.7
40~60	1.4	1.7	1.8	1.8	2.0	2.4	2.8
60~80	1.4	1.8	1.8	1.9	2.1	2.5	2.9

Other Properties	
Photoelastic Constant $\beta$ nm/(cm·10 <sup>9</sup> Pa)	2.32
Specific Gravity d	2.89
Remarks	

OHARA 23-05

OHARA Copyright© OHARA INC. All Rights Reserved.

※The name of the glass type is the model number assigned based on the main components of the composition: large, medium, small refractive index and serial number.