

S-LAL12

Code(d) **678553**

Code(e) **681551**

Refractive Index n_d	1.67790	Abbe Number ν_d	55.34	Dispersion n_F-n_C	0.012250
Refractive Index n_e	1.677900	Abbe Number ν_e	55.08	Dispersion $n_F-n_{C'}$	0.012361

Refractive Indices		
$\lambda(\mu m)$		
n_{2325}	2.32542	1.64414
n_{1970}	1.97009	1.65021
n_{1530}	1.52958	1.65669
n_{1129}	1.12864	1.66242
n_t	1.01398	1.66433
n_s	0.85211	1.66768
$n_{A'}$	0.76819	1.66998
n_f	0.70652	1.67208
n_C	0.65627	1.67419
$n_{C'}$	0.64385	1.67478
n_{He-Ne}	0.6328	1.67533
n_D	0.58929	1.67779
n_d	0.58756	1.67790
n_e	0.54607	1.68082
n_F	0.48613	1.68644
$n_{F'}$	0.47999	1.68714
n_{He-Cd}	0.44157	1.69225
n_g	0.435835	1.69314
n_h	0.404656	1.69872
n_i	0.365015	1.70826

Constants of Dispersion Formula	
A_1	9.92053895E-01
A_2	7.71377731E-01
A_3	1.18296264E+00
B_1	1.67095063E-02
B_2	2.36750156E-03
B_3	1.05901080E+02

Chemical Properties	
Water Resistance(Powder) Group RW(P)	2
Acid Resistance(Powder) Group RA(P)	5
Weathering Resistance(Surface) Group W(S)	2
Acid Resistance(Surface) Group SR	53.0
Phosphate Resistance PR	4.2

Mechanical Properties	
Young's Modulus E (GPa)	91.0
Rigidity Modulus G (GPa)	35.4
Poisson's Ratio σ	0.284
Knoop Hardness Hk[Class]	560 6
Abrasion Aa	166

Partial Dispersions	
n_C-n_t	0.009855
$n_C-n_{A'}$	0.004212
n_d-n_C	0.003712
n_e-n_C	0.006632
n_g-n_d	0.015241
n_g-n_F	0.006703
n_h-n_g	0.005580
n_i-n_g	0.015119
n_C-n_t	0.010445
$n_e-n_{C'}$	0.006042
$n_{F'}-n_e$	0.006319
$n_i-n_{F'}$	0.021121

Relative Partial Dispersions	
$\theta_{C,t}$	0.8045
$\theta_{C,A'}$	0.3438
$\theta_{d,C}$	0.3030
$\theta_{e,C}$	0.5414
$\theta_{g,d}$	1.2442
$\theta_{g,F}$	0.5472
$\theta_{h,g}$	0.4555
$\theta_{i,g}$	1.2342
$\theta'_{C,t}$	0.8450
$\theta'_{e,C}$	0.4888
$\theta'_{F,e}$	0.5112
$\theta'_{i,F'}$	1.7087

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta \theta_{C,t}$	-0.0018
$\Delta \theta_{C,A'}$	0.0008
$\Delta \theta_{g,d}$	-0.0056
$\Delta \theta_{g,F}$	-0.0047
$\Delta \theta_{i,g}$	-0.0274

Thermal Properties	
Strain Point StP (°C)	604
Annealing Point AP (°C)	630
Transformation Temperature Tg (°C)	652
Yield Point At (°C)	679
Softening Point SP (°C)	716
Expansion Coefficients (-30~+70°C)	72
α (10 ⁻⁷ K ⁻¹) (+100~+300°C)	86
Thermal Conductivity λ W/(m·K)	0.717

Coloring			
λ_{80}	360	λ_5	285
λ_{70}			

Internal transmission			
$\lambda_{0.80}$	337	$\lambda_{0.05}$	279

CCI		
B	G	R
0.00	0.26	0.24

Internal Transmittance	
$\lambda(nm)$	τ 10mm
280	0.06
290	0.15
300	0.29
310	0.45
320	0.61
330	0.73
340	0.83
350	0.89
360	0.938
370	0.962
380	0.976
390	0.984
400	0.988
420	0.992
440	0.994
460	0.995
480	0.997
500	0.998
550	0.999
600	0.998
650	0.998
700	0.998
800	0.999
900	0.997
1000	0.996
1200	0.996
1400	0.991
1600	0.991
1800	0.981
2000	0.963
2200	0.901
2400	0.73

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	$\Delta n / \Delta T$ relative (10 ⁻⁶ K ⁻¹)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	0.4	0.6	0.7	0.8	0.9	1.2	1.5
-20~ 0	0.5	0.7	0.7	0.8	1.0	1.3	1.7
0~20	0.5	0.8	0.8	0.9	1.1	1.4	1.8
20~40	0.5	0.8	0.9	1.0	1.1	1.5	1.9
40~60	0.5	0.9	0.9	1.1	1.2	1.6	2.0
60~80	0.6	1.0	1.0	1.1	1.3	1.7	2.1

Other Properties	
Photoelastic Constant β nm/(cm·10 ⁵ Pa)	1.61
Specific Gravity d	4.01
Remarks	

OHARA 23-05

OHARA Copyright© OHARA INC. All Rights Reserved.

※The name of the glass type is the model number assigned based on the main components of the composition: large, medium, small refractive index and serial number.