

S-PHM53

Code(d) **603655**

Code(e) **605651**

Refractive Index n_d	1.60300	Abbe Number ν_d	65.44	Dispersion n_F-n_C	0.009215
	1.603001				
Refractive Index n_e	1.605200	Abbe Number ν_e	65.15	Dispersion n_F-n_C'	0.009289

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1.57583
n_{1970}	1.97009	1.58092
n_{1530}	1.52958	1.58634
n_{1129}	1.12864	1.59103
n_t	1.01398	1.59256
n_s	0.85211	1.59519
$n_{A'}$	0.76819	1.59697
n_f	0.70652	1.59858
n_C	0.65627	1.60019
$n_{C'}$	0.64385	1.60064
$n_{\text{He-Ne}}$	0.6328	1.60106
n_D	0.58929	1.60292
n_d	0.58756	1.60300
n_e	0.54607	1.60520
n_F	0.48613	1.60940
$n_{F'}$	0.47999	1.60993
$n_{\text{He-Cd}}$	0.44157	1.61372
n_g	0.435835	1.61438
n_h	0.404656	1.61850
n_i	0.365015	1.62547

Constants of Dispersion Formula	
A_1	1.09775423E+00
A_2	4.34816432E-01
A_3	1.13894976E+00
B_1	1.23369400E-02
B_2	-3.72522903E-04
B_3	1.24276984E+02

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	5
Weathering Resistance(Surface) Group W(S)	1~2
Acid Resistance(Surface) Group SR	51.0
Phosphate Resistance PR	4.0

Mechanical Properties	
Young's Modulus E (GPa)	70.8
Rigidity Modulus G (GPa)	27.5
Poisson's Ratio σ	0.285
Knoop Hardness Hk(Class)	390 4
Abrasion Aa	407

Partial Dispersions	
n_C-n_t	0.007630
$n_C-n_{A'}$	0.003223
n_d-n_C	0.002812
n_e-n_C	0.005011
n_g-n_d	0.011380
n_g-n_F	0.004977
n_h-n_g	0.004114
n_i-n_g	0.011090
n_C-n_t	0.008078
$n_e-n_{C'}$	0.004563
$n_{F'}-n_e$	0.004726
$n_i-n_{F'}$	0.015545

Relative Partial Dispersions	
$\theta_{C,t}$	0.8280
$\theta_{C,A'}$	0.3498
$\theta_{d,C}$	0.3052
$\theta_{e,C}$	0.5438
$\theta_{g,d}$	1.2349
$\theta_{g,F}$	0.5401
$\theta_{h,g}$	0.4464
$\theta_{i,g}$	1.2035
$\theta'_{C,t}$	0.8696
$\theta'_{e,C}$	0.4912
$\theta'_{F,e}$	0.5088
$\theta'_{i,F'}$	1.6735

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta \theta_{C,t}$	-0.0257
$\Delta \theta_{C,A'}$	-0.0054
$\Delta \theta_{g,d}$	0.0061
$\Delta \theta_{g,F}$	0.0045
$\Delta \theta_{i,g}$	0.0265

Thermal Properties	
Strain Point StP (°C)	-
Annealing Point AP (°C)	-
Transformation Temperature Tg (°C)	610
Yield Point At (°C)	644
Softening Point SP (°C)	681
Expansion Coefficients (-30~+70°C)	93
α (10^{-7}K^{-1}) (+100~+300°C)	109
Thermal Conductivity λ W/(m·K)	0.615

Coloring			
λ_{80}	360	λ_5	300
λ_{70}			

Internal transmission			
$\lambda_{0.80}$	362	$\lambda_{0.05}$	313

CCI		
B	G	R
0.00	0.56	0.52

Internal Transmittance	
$\lambda(\text{nm})$	τ 10mm
280	
290	
300	
310	0.03
320	0.10
330	0.25
340	0.45
350	0.64
360	0.78
370	0.88
380	0.935
390	0.963
400	0.977
420	0.986
440	0.987
460	0.989
480	0.992
500	0.994
550	0.998
600	0.997
650	0.996
700	0.996
800	0.997
900	0.997
1000	0.996
1200	0.997
1400	0.993
1600	0.987
1800	0.967
2000	0.941
2200	0.87
2400	0.83

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	$\Delta n/\Delta T$ relative (10^{-6}K^{-1})						
	t	C'	He-Ne	D	e	F'	g
-40~-20	-3.1	-2.8	-2.8	-2.7	-2.6	-2.4	-2.2
-20~ 0	-3.0	-2.8	-2.8	-2.7	-2.6	-2.4	-2.1
0~20	-3.0	-2.7	-2.7	-2.6	-2.5	-2.3	-2.0
20~40	-2.9	-2.6	-2.6	-2.5	-2.4	-2.1	-1.9
40~60	-2.9	-2.5	-2.5	-2.4	-2.2	-1.9	-1.7
60~80	-2.7	-2.3	-2.3	-2.2	-2.0	-1.7	-1.5

Other Properties	
Photoelastic Constant β nm/(cm·10 ⁹ Pa)	1.21
Specific Gravity d	3.51
Remarks	

OHARA 23-05

OHARA Copyright© OHARA INC. All Rights Reserved.

※The name of the glass type is the model number assigned based on the main components of the composition: large, medium, small refractive index and serial number.